

Elysian

Technical Data

Stain Resistance CFFA 141 - 2012 and ASTM D 1308-02(2013) alta by Applied Textiles

	Wipe with dry cloth	Water only cleaning	Detergent based cleaner	Solvent based cleaner
Coca Cola	5.0			
Coffee	1.0	4.0	5.0	
Italian Dressing	3.0	3.0	5.0	
Orange Juice	3.0	5.0		
Pen (Ball Point)	1.0	2.0	5.0	
Red Wine	1.0	3.0	5.0	
Suntan Oil	1.0	1.0	3.0	4.0

5 No evidence of stain present | 4 Slight evidence | 3 Noticeable evidence | 2 Considerable evidence | 1 Excessive evidence

Martindale40,000Wyzenbeek100,000 cyclesFire RetardantNFPA 260 and Cal 117Composition100% PESWeight220gr/m²Width148cmMin. usable width138cm

Pilling5Seam Slippage Warp4mmSeam Slippage Weft3mmColor Fastness : Light5Color Fastness : Rubbing Wet4Color Fastness : Rubbing Dry4/5

Usage















Care



Cleaning (US)

W